KONIX PP-400

Polyether Polyol

Technical Data Sheet

General

KONIX* PP-400 is a 400 molecular weight polyether diol having excellent compatibility with organic chemicals. This grade have high purity and the narrow polymerization degree distribution.

KONIX PP-400 is used in an intermediate for the production of polyurethane elastomers, coatings and adhesives and specialty foams. It is manufactured to close specifications ensuring a high degree of consistency.

Product Specifications

Items	*Specifications*
Appearance	Clear Liquid
Color (APHA No.)	50 max.
Water content (wt%)	0.05 max.
Hydroxyl Number (mg KOH/g)	265 - 295
Viscosity at 25℃ (cps)	50 - 90
Acid number (mg KOH/g)	0.05 max.
pH	5.0 – 7.0

Health & Safety Information

KONIX PP-400 is very low odor of acute toxicity and is neither irritating nor sensitive to the skin. It is a chemical for industrial use and normal care should be taken to avoid unnecessary contacts, splashes in the eyes or accidental ingestion. . (For more information, refer to Material Safety Data Sheet (MSDS))

Storage

KONIX PP-400 is slightly hygroscopic and must be stored under conditions that contamination with water and the absorption of atmospheric moisture are prevented. Contact with copper alloys must be avoided.

KONIX PP-400 should be stored in dry conditions away from direct source of heat, preferably in the unopened original containers. Open drums must be capped immediately after drawing-off the material.

Recommended maximum storage time ---------- 12 months

storage temperatures ---------- 20 ~ 60 ℃

* 'KONIX' & 'NIXOL' are registered trademark of KPX Chemical Co., Ltd..

▶ Homepage : www.kpxchemical.com

▶ HEAD OFFICE (SEOUL KOREA) Tel) +82-2-2014-4000, Fax) +82-2-362-0034

▶ ULSAN PLANT, R & D CENTER (ULSAN KOREA) Tel) +82-52-279-0200, Fax) +82-52-268-6410

Packing

KONIX PP-400 is supplied in steel drums (or bulk container)

Average Net Weight ---------- 200 kg
Average Gross Weight ---------- 219 kg

Viscosity (vs.Temperature)



Temperature,℃	Viscosity, cps
10	210
30	54
50	19
70	8
100	7

Specific gravity (vs.Temperature)



Temperature,℃	Specific gravity, g/cm³
20	1.0090
30	1.0015
50	0.9855
70	0.9700

This information is furnished without warranty, express or otherwise. In all case, It is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose. KPX CHEMICAL Co., LTD. assumes no legal responsibility for use of or reliance upon this information.

* 'KONIX' & 'NIXOL' are registered trademark of KPX Chemical Co., Ltd..

▶ HEAD OFFICE (SEOUL KOREA) Tel) +82-2-2014-4000, Fax) +82-2-362-0034
▶ ULSAN PLANT, R & D CENTER (ULSAN KOREA) Tel) +82-52-279-0200, Fax) +82-52-268-6410